

need

X

Union of Soviet  
Socialist Republics

**SPECIFICATION OF INVENTION  
FOR PATENT**

(11)

322960

(61) Dependant on patent ---

State Committee, USSR  
Council of Ministers on  
Inventions and Discoveries

(22) Filed 07.21.69 (21) 1347251/23-26  
with addition of application no. ---  
(32) Priority ---  
Published 01.05.75 Bulletin No. 1

(51) Int. Cl. C 01g 23/04

(53) UDC 546.824-31.07  
(088.8)

Publication date of the specification 02.12.75

(72) Inventors:

V. I. Mil'ko, M. F. Zhukov, P. P. Isay, M. A. Gorovay, N. P. Shaburov,  
V. I. Borodin, G. Yu. Dautov, S. B. Aleskovskiy, V. P. Pundrovskiy,  
Yu. S. Dudnikov and Yu. I. Sukhinin

(71) Applicant:

All-Union Scientific Research and Design Institute of Titanium

**(54) METHOD OF PRODUCING TITANIUM DIOXIDE**

There is a known method for producing titanium dioxide by oxidizing titanium tetrachloride in oxygen-containing plasma. In this case, oxygen is heated in a high-frequency gas discharge. However, this method is complicated due to the complex system for creating an oxygen-containing plasma.

In order to simplify the process, it is proposed to heat the oxygen-containing gas in a stabilized electric arc.

Atmospheric air with the dust removed is used as the plasma-forming gas. The air plasma is produced in electric arc heaters. To improve the mixing, three plasma jets are introduced into the reaction zone such that the jets form a plasma funnel, into which is introduced finely atomized liquid  $TiCl_4$ . The reacting flow at speed of 700 m/s passes through a quenching nozzle into a cooled volume. From the cooled volume, the dust-containing mixture is directed to a system for trapping the  $TiO_2$ .

Tests are conducted with 20% oxygen excess, temperature of the air plasma at the entry to the reaction zone 3000-3200°K; temperature in the reaction zone 2200-2300°K; dwell time for the reagents in the reaction zone  $2 \cdot 10^{-3}$  s; outlay of electricity 2-3 kWh/kg of  $TiO_2$ . The resulting titanium dioxide contains 87-97% rutile without introduction of rutilizing additives, the  $TiO_2$  particle diameter is 0.1-0.4  $\mu$ ; the particle shape is spherical and oval (electron microscope analysis).

The chlorine gas leaving the titanium dioxide trapping system contains around 25 vol. % of chlorine. The chlorine gas is used to produce chlorine derivatives. A mixture of oxygen and air (70% oxygen, 30% air) is used as the plasma-forming gas, which makes it possible to reduce the outlay of energy for production of titanium dioxide to 1.3-1.5 kWh/kg of  $TiO_2$  and obtain concentrated chlorine gas (chlorine content around 70 vol. %). Such chlorine gas can be used for chlorination of titanium-containing raw material.

**Patent claim**

Method of production of titanium dioxide by oxidizing titanium tetrachloride in oxygen-containing plasma, characterized in that, to simplify the process, the oxygen-containing gas is heated in a stabilized electric arc.

[printing press information - not translated]